

COREWELD A650R

Flux cored wires [FCAW]

Hardfacing and repairing

CLASSIFICATION:	APPROVALS:	APPLICATION:
EN ISO 14700-A : T Fe8 DIN 8555 : MF 6-GF-60GP		Hardfacing and repairing Mining

- Flux cored wire recommended for hardfacing of elements exposed to high impact and medium and high abrasion, as well as metal-to-metal wear.
- The build-up weld is hard, smooth, without microcracks, resistant to distortion and impact. It can only be machined by grinding.
- The weld deposit after hardfacing in the first layer reaches a hardness of approx. 60 HRC.
- It can be used in TIG technology.
- Possibility of hardfacing thinner elements with complex shapes.
- Martensitic structure.

Application

Regeneration of elements in the mining industry, construction, metallurgy, agriculture

Base material

Steels


Cast steels

Typical chemical composition %

C	Si	Mn	Cr	W
0,45	1,5	0,50	6,80	0,80

Typical mechanical properties

Hardness	57-62 HRC / The hardness of the build-up weld depends on the relevant welding conditions, the number of layers and the chemical composition of the base material. /
-----------------	---

Welding current	
------------------------	---

Welding positions	
--------------------------	---

Shielding gases acc. to EN ISO 14175	M21 - Ar + 15 - 25% CO2 / C1 - 100% CO2 /
---	---

Welding parameters and packing

Ø	Welding current [A]	Voltage [V]	Gas flow	Weight of packet [kg]
1,2	180-360	22-34	20-25	15,0
1,6	180-450	22-40	20-25	15,0

METALWELD-FIPROM POLSKA spółka z o.o.

ul. Mikołajczyka 57, 41-200 Sosnowiec

+48 (32) 297 75 50 - 51

+48 (32) 297 75 88

